

1988

Acrylic-Styrene Copolymer Emulsion

Product Description

1988 Exposed Waterproofing Emulsion is an acrylate-styrene copolymer emulsion designed for exposed metal roofing waterproof coatings, base adhesives for metal colored stone tiles, and single-component waterproofing. It delivers excellent substrate adhesion, outstanding elongation at break and tensile strength, superb water resistance, low-temperature flexibility, and great elastic recovery. Its high mechanical stability allows for direct powder dispersion during formulation.

Product Features

- Excellent substrate adhesion, elongation at break, and tensile strength.
- Superb water resistance, low-temperature flexibility, and great elastic recovery.
- High mechanical stability.

Physical Properties*

Properties	Value	Unit	Test Method
Appearance	Milky white with a slight blue tint	—	Visual
Solid Content	50 ± 1	wt%	GB/T 20623-2006
pH	8.0 - 9.0	—	GB/T 20623-2006

Viscosity	3000 - 6000	CPS	Brookfield DV-S, 4#, 30rpm, 25°C
Glass Transition Temperature (TG)	-20	°C	—

*Note: *The properties listed above represent typical results only and should not be construed as product specifications. Please refer to the specific Certificate of Analysis (COA) for official specifications.*

Storage

Please store this product in a cool, dry place away from direct sunlight. The storage temperature should be maintained between 5°C and 35°C. Keep the original packaging completely intact.

The shelf life of this product is six months from the date of manufacture. If the product exceeds its shelf life, a performance evaluation is highly recommended before use. Once the packaging is opened, it is recommended to filter the emulsion properly before application and consume it as quickly as possible.

Disclaimer

Shandong Sanjia Polymer Material Co., Ltd. strongly recommends that customers handle and use this product safely and rationally in accordance with the detailed information provided in the Material Safety Data Sheet (MSDS). While we believe the recommendations and data contained herein are true and reliable, the contents of this Technical Data Sheet are provided for reference purposes only. We offer no warranties, whether express or implied, regarding product characteristics, applications, quality, safety, product specifications, merchantability, or fitness for a particular purpose.

Shandong Sanjia Polymer Material Co., Ltd.